

FACETED EPOXY COLOR

1	2	3	4	5	6	7	8	9	10	11	12
13	14	15	16	17	18	19	20	21	22	23	24
25	26	27	28	29	30	31	32	33	34	35	36
37	38	39	40	41	42	43	44	45	46	47	48
								*			
49	50	51	52	53	54	55	56	57	58	59	60
61	62	63	64	65	66	67	68	69	70	71	72
				*	*	*	*	*	*	*	*

** Color tone can be changeable depending on production time.

** Conditions for Pressing Faceted Epoxy (Back side)

Pressure : 2.8~3.0kg

Temperature : 160~170℃

Time : 8~10 seconds (small size) more than 15seconds (big size)